

POP PICALTAL S POWDER

Eco friendly non-swelling pickling agent
(Reduces pickling time by almost half)

Pop Picaltal S Powder does not swell the pelt and can, therefore, be applied with 1-2% of any salt.

Pop Picaltal S Powder does not swell the pelt and can, therefore, be applied with 1-2% of any salt.

Nature :. Mixture of aromatic sulphonic acid with organic compounds

Appearance : Off White powder

pH of 10% solution : 0.75 approx.

Pop Picaltal S Powder is hygroscopic. On prolonged exposure to air, the product absorbs some moisture which will not impair the effectiveness of the product.

By using Pop Picaltal S Powder it is possible to carry out pickling and chrome tanning with just 1-2% of any salt. The skin enters the tanning process in its natural plumped condition. As a result, a more uniform and more intensified penetration of the tannin by the pelt is achieved, so that leathers with exceptional fullness a fine, smooth grain and mellow handle are obtained. It can also be used for water proof leather.

APPLICATION

	30-40% water.	- aaaaaa	
	1.0-2.0% Common Salt	- Run for 10 mins.	
Add :	3.0-4.0% PsOP PICALTAL S Powder	- Run for 2-4 hrs.	
Add :	6.0-7.0% Basic Chrome Sulphate	- Run for 2-3 hrs.	
Add :	100%	- Water	
Add :	0.3-0.5% - POPTAN BFR	- Run for 6 hrs.	pH 3.8-4.0

ADVANTAGES

- Reduces pickling time by almost half.
- Leathers with exceptional fullness, a fine, smooth grain and mellow handle are obtained.
- No addition of sulphuric acid is required and hence reduces mineral salts in effluent. So effluent is eco-friendly.
- Better uptake and exhaustion of chrome by which it reduces chrome consumption.
- Safe and easy in application.



Without Gurantee