

POPSYNTH SL 47 POWDER

Synthetic Fatliquor for all type of skins .

Appearance : Light Yellow Brown Opalescent viscous Liquid .

Chemical Character : Blend of high molecular sulphited synthetic esters , solvent and long Chain alkanes .

pH of 10% solution : 8.0 + 0.5

Stability : Stable at normal pH conditions to neutral salts , basis , acids , mineral salts and concentrations normally used in tanneries .

Compatibility : Compatible with Anionic dyes , fat liquors as well as synthetic and vegetable tanning agents .

Dissolution : Before adding to the floats , dilute with warm water until obtaining fluid consistency.

Fastness of light : Good

PROPERTIES: **Popsynth SL-47** is a light fast fat liquor based on synthetic sulphited esters, solvent and long chain alkanes .

Popsynth SL-47 is highly penetrative fat liquor with high fat content and imparts excellent softness and body to leather .

Popsynth SL-47 is an ideal fat liquor in the sense , besides giving the uniform lubrication it also paves the way for the uniform distribution and absorption of the syntans , dyes and the other chemicals which are added subsequently .

Popsynth SL-47 imparts full and soft feel to the leather without over fatliquoring and gives very warm and pleasant feel to the leather surface . It also imparts good smoothness to the leather surface .

APPLICATIONS:

Popsynth SL-47 is ideally suited for light weight leathers VIZ . Napps , Gloving and clothing leathers .

Popsynth SL-47 can be best applied immediately after neutralization at an offer of 1 to 3% for light weight leathers , followed by normal retannage and fatliquoring . It redistributes the natural fat present in the leather .

Popsynth SL-47 can be recommended for all types of leather , especially for shoe uppers, nubuck leathers , glazed kid goat uppers , garment or bag leathers and all type of seudes .

STORAGE :

Popsynth SL-47 can be stored for about one year under normal conditions and temperatures . The product should always be stirred before use as a precautionary measure due to temperature changes .



Without Gurantee