

POPLON CHEMIE

Manufacturers of: LEATHER CHEMICALS & TEXTILE AUXILIARIES

An ISO 9001-2015 Certified Company

I/S Nijjarpura Village, G.T. Road
Amritsar-143001 INDIA
www.poplonchemie.com
poplonchemie@hotmail.com
sunilbehal@poplonchemie.com

Cell : +91 9815003892
Telefax : +91 183 2226029

POP MIMOSA FS

POP MIMOSA FS is a soft mimosa double bleach extract which is suitable to any kind of vegetable leather. It is excellent for pit-drum or drum tannage and also for the retannage of chrome leather.

TYPICAL ANALYSIS :

Physical Aspect	:	Light Brown Powder
Ionic Character	:	Anionic
PCP	:	Free
Tannins %	:	68% \pm 1
Non-Tannins %	:	27%
Moisture %	:	7% maximum.
pH (1:10 soln.)	:	4.4 – 4.8
Ash Content	:	3.5% maximum
Insolubles	:	2%
Iron	:	50 ppm max.

PROPERTIES :


POP MIMOSA FS is soluble in tap and hot water, with the following characteristics on vegetable tannage :

- Efficient penetration.
- Excellent yield.
- Good fixation

For retannage of chrome leather **POP MIMOSA FS** permits :

- Bellies and flanks fillings.
- Better buffing properties.
- Excellent polish effect.
- To keep the embossing effect.

Contd.....2.....



POPLON CHEMIE

Manufacturers of: LEATHER CHEMICALS & TEXTILE AUXILIARIES

An ISO 9001-2015 Certified Company

I/S Nijjarpura Village, G.T. Road
Amritsar-143001 INDIA
www.poplonchemie.com
poplonchemie@hotmail.com
sunilbehal@poplonchemie.com

Cell : +91 9815003892
Telefax : +91 183 2226029

.....2.....

APPLICATION :

POP MIMOSA FS may be used alone or blended with other vegetable extracts. The following use is recommended :

- Based on limed weight
 - 25-30% for vachetta tannage (veg leather)
 - 40-45% for sole tannage.
- Based on shaved weight
 - 5-15% of **POP MIMOSA FS** for chrome leather tannage.

TYPES OF MANUFACTURE :

- Flexible and semi firm leather.
- Tanning and Re-tanning of chrome box-cow.
- Harness and calf leather.
- East Indian leather.

RECOMMENDATION :

During the leather production, there may be a risk of iron contamination. In order to prevent this, we suggest to use an iron-sequestering agent (0.2% on the reference weight), which may be added together with the first addition of tanning agents on the tanning or retanning processes.

STORAGE :

POP MIMOSA FS maintains its characteristics unchanged if properly stored in dry premises protected from sunlight in closed bags.

PACKING :

POP MIMOSA FS is presented in a powder form, dedusted, and packed in a 25Kg. bag net weight.
