

POPLON CHEMIE

Manufacturers of: LEATHER CHEMICALS & TEXTILE AUXILIARIES

An ISO 9001-2015 Certified Company

I/S Nijjarpura Village, G.T. Road

Amritsar-143001 INDIA

www.poplonchemie.com

poplonchemie@hotmail.com

sunilbehal@poplonchemie.com

Cell : +91 9815003892

Telefax : +91 183 2440892

POP MIMOSA MS

POP MIMOSA MS is a soft mimosa single bleached extract of high quality indicated for tannage of hides and skins whenever a very light colour is required. In the tannage of soles and vachettas a very nice beige tone, often desired, is achieved.

TYPICAL ANALYSIS :

Physical Aspect	:	Light beige hygroscopic powder, dedusted.
Ionic Character	:	Anionic
PCP	:	Free
Tannins %	:	68.0% \pm 1.0
Non-Tannins %	:	25%
Insolubles	:	0.5%
Moisture %	:	4.0%
Mineral Ash	:	0.4%
Fe (Iron)	:	0.00025 ppm
Cu (Copper)	:	Nil
pH (1:10 soln.)	:	4.0-4.5

PROPERTIES :


POP MIMOSA MS is soluble in tap and hot water, with the following characteristics on vegetable tannage :

- Fast and efficient penetration.
- Excellent yield.
- Very light colour leathers
- Good fixation
- Nice beige tone

For chrome leather tannage **POP MIMOSA MS** permits :

- Bellies and flanks fillings.
- Better buffing properties.
- Excellent polish effect.
- To keep the embossing effect.

Contd.....2.....



POPLON CHEMIE

Manufacturers of: LEATHER CHEMICALS & TEXTILE AUXILIARIES

An ISO 9001-2015 Certified Company

I/S Nijjarpura Village, G.T. Road

Amritsar-143001 INDIA

www.poplonchemie.com

poplonchemie@hotmail.com

sunilbehal@poplonchemie.com

Cell : +91 9815003892

Telefax : +91 183 2440892

.....2.....

APPLICATION :

POP MIMOSA MS may be used alone or blended with other vegetable extracts. The following use is recommended :

- Based on limed weight
 - 25-30% for vachetta tannage (veg leather)
 - 40-45% for sole tannage.
- Based on shaved weight
 - 5-15% for chrome leather tannage.

TYPES OF MANUFACTURE :

- Flexible and semi firm leather.
- Tanning and Re-tanning of chrome box-cow.
- Harness and calf leather.
- East Indian leather.

RECOMMENDATION :

During the leather production, there may be a risk of iron contamination. In order to prevent this, we suggest to use an iron-sequestering agent such as Pop DS Powder (0.2% on the reference weight), which may be added together with the first addition of tanning agents on the tanning or retanning processes.

STORAGE :

POP MIMOSA MS maintains its characteristics unchanged if properly stored in dry premises protected from sunlight in closed bags.

PACKING :

POP MIMOSA MS is presented in a powder form, dedusted, and packed in a 25Kg. bag net weight.
